

Spectroscopic study of the effect of N and F codoping on the spatial distribution of Er³⁺ dopant ions in vitreous SiO₂

Gubaidullin R., Orlinskii S., Rakhmatullin R., Sen S.
Kazan Federal University, 420008, Kremlevskaya 18, Kazan, Russia

Abstract

Pulsed electron paramagnetic resonance (EPR) spectroscopy has been used to study the influence of codoping with N and/or F on the clustering of Er³⁺ ions in vitreous SiO₂. Measurements of echo-detected EPR, spin-lattice and phase memory relaxation times, and electron spin-echo envelope modulation (ESEEM) were made in the X band. Er-N, Er-F, and Er--F codoped glasses show clear evidence of clustering of Er³⁺ ions at concentration levels ranging between $6.67 \times 10^{18} \text{ cm}^{-3}$ and $6.67 \times 10^{19} \text{ cm}^{-3}$. However, the relatively long phase memory relaxation time and the observability of ESEEM in the Er-N-F codoped glass strongly indicate that combined codoping with N and F is more effective in homogenization of the spatial distribution of Er³⁺ ions in vitreous SiO₂, although, the structural mechanism remains unclear. The ESEEM results provide evidence in favor of the presence of N in the vicinity of the Er³⁺ ions in Er-N-F codoped vitreous SiO₂. © 2007 American Institute of Physics.

<http://dx.doi.org/10.1063/1.2713351>
